

**PCT**WORLD INTELLECTUAL PROPERTY ORGANIZATION  
International Bureau

## INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

<b>(51) International Patent Classification <sup>5</sup> :</b> <b>C08F 210/02, C08L 23/08</b>	<b>A2</b>	<b>(11) International Publication Number:</b> <b>WO 94/17112</b> <b>(43) International Publication Date:</b> 4 August 1994 (04.08.94)
<b>(21) International Application Number:</b> PCT/US94/01052 <b>(22) International Filing Date:</b> 28 January 1994 (28.01.94)  <b>(30) Priority Data:</b> 08/010,958      29 January 1993 (29.01.93)      US  <b>(71) Applicant:</b> THE DOW CHEMICAL COMPANY [US/US]; 2030 Dow Center, Abbott Road, Midland, MI 48640 (US).  <b>(72) Inventors:</b> KOLTHAMMER, Brian, W., S.; 109 Rosewood Street, Lake Jackson, TX 77566 (US). CARDWELL, Robert, S.; 106 Any Way, Lake Jackson, TX 77566 (US).  <b>(74) Agent:</b> WARRICK, Noreen, D.; The Dow Chemical Company, Patent Department, Building B-1211, Freeport, TX 77541 (US).		<b>(81) Designated States:</b> AU, BB, BG, BR, BY, CA, CN, CZ, FI, HU, JP, KR, KZ, LK, LU, LV, MG, MN, MW, NO, NZ, PL, PT, RO, RU, SD, SK, UA, UZ, European patent (AT, BE, CH, DE, DK, ES, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE).  <b>Published</b> <i>Without international search report and to be republished upon receipt of that report.</i>
<b>(54) Title:</b> ETHYLENE INTERPOLYMERIZATIONS  <b>(57) Abstract</b>  Processes for polymerizing ethylene/a-olefin interpolymer compositions are disclosed. The interpolymer compositions have a controlled composition and a controlled molecular weight distribution. The processes utilize a highly-efficient homogeneous catalyst composition in at least one reactor to produce a first interpolymer having a narrow composition distribution and a narrow molecular weight distribution, and a highly-efficient heterogeneous Ziegler catalyst in at least one other reactor. The reactors can be operated sequentially or separately, depending upon the desired product. The novel compositions have good optical properties (e.g., clarity and haze) and good physical properties (e.g., modulus, yield strength, toughness and tear). Useful products which can be formed from these compositions include film, molded articles and fiber.		

**FOR THE PURPOSES OF INFORMATION ONLY**

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AT	Austria	GB	United Kingdom	MR	Mauritania
AU	Australia	GE	Georgia	MW	Malawi
BB	Barbados	GN	Guinea	NE	Niger
BE	Belgium	GR	Greece	NL	Netherlands
BF	Burkina Faso	HU	Hungary	NO	Norway
BG	Bulgaria	IE	Ireland	NZ	New Zealand
BJ	Benin	IT	Italy	PL	Poland
BR	Brazil	JP	Japan	PT	Portugal
BY	Belarus	KE	Kenya	RO	Romania
CA	Canada	KG	Kyrgyzstan	RU	Russian Federation
CF	Central African Republic	KP	Democratic People's Republic of Korea	SD	Sudan
CG	Congo	KR	Republic of Korea	SE	Sweden
CH	Switzerland	KZ	Kazakhstan	SI	Slovenia
CI	Côte d'Ivoire	LI	Liechtenstein	SK	Slovakia
CM	Cameroon	LK	Sri Lanka	SN	Senegal
CN	China	LU	Luxembourg	TD	Chad
CS	Czechoslovakia	LV	Latvia	TG	Togo
CZ	Czech Republic	MC	Monaco	TJ	Tajikistan
DE	Germany	MD	Republic of Moldova	TT	Trinidad and Tobago
DK	Denmark	MG	Madagascar	UA	Ukraine
ES	Spain	ML	Mali	US	United States of America
FI	Finland	MN	Mongolia	UZ	Uzbekistan
FR	France			VN	Viet Nam
GA	Gabon				

ETHYLENE INTERPOLYMERIZATIONS

This invention relates to ethylene interpolymers and  
5 interpolymerization processes. The processes utilize at least one  
homogeneous polymerization catalyst and at least one heterogeneous  
polymerization catalyst in separate reactors connected in series or in  
parallel. Interpolymers produced from such processes are thermoplastic  
and have surprisingly beneficial properties, including improved impact and  
10 tear properties, high modulus and higher crystallization temperatures, and  
are useful in making molded or shaped articles, film, and the like.

There are known several polymerization processes for producing  
polyethylene and ethylene interpolymers, including suspension, gas-phase  
15 and solution processes. Of these, the solution process is of commercial  
significance due to the advantages described in U.S. Pat. 4,330,646  
(Sakurai et al.). A most advantageous solution process would be found if  
the temperature of the polymerization solution could be increased and the  
properties of the polymers suitably controlled. U.S. Pat No. 4,314,912  
20 (Lowery et al.) describes a Ziegler-type catalyst suitable for use in high  
temperature solution polymerization processes. U.S. Pat No. 4,612,300  
(Coleman, III) and USP 4,330,646 describe a catalyst and solution  
polymerization process for producing polyethylenes having a narrow  
molecular weight distribution. USP 4,330,646 also describes a process for  
25 producing polyethylenes with a broader molecular weight distribution in a  
solution process. These processes are based on heterogeneous Ziegler type  
catalysts which produce interpolymers with broad composition distributions  
regardless of their molecular weight distribution. Such ethylene polymers  
have deficiencies in some properties, for instance, poor transparency and  
30 poor anti-blocking properties.

Solution polymerization processes for producing ethylene  
interpolymers with narrow composition distributions are also known. U.S.  
Pat No. 4,668,752 (Tominari et al.) describes the production of  
heterogeneous ethylene copolymers with characteristics which include a  
35 narrower composition distribution than conventional heterogeneous  
copolymers. The utility of such polymer compositions in improving  
mechanical, optical and other important properties of formed or molded

objects is also described. The complex structures of the copolymers necessary to achieve such advantages are finely and difficultly controlled by nuances of catalyst composition and preparation; any drift in which would cause a significant loss in the desired properties. U.S. Pat No. 5 3,645,992 (Elston) describes the preparation of homogeneous polymers and interpolymers of ethylene in a solution process operated at temperatures of less than 100°C. These polymers exhibit a "narrow composition distribution", a term defined by a comonomer distribution that within a given polymer molecule and between substantially all molecules of the 10 copolymer is the same. The advantages of such copolymers in improving optical and mechanical properties of objects formed from them is described. These copolymers, however, have relatively low melting points and poor thermal resistance.

U.S. Pat No. 4,701,432 (Welborn, Jr.) describes a catalyst 15 composition for the production of ethylene polymers having a varied range of composition distributions and/or molecular weight distributions. Such compositions contain a metallocene and a non-metallocene transition metal compound supported catalyst and an aluminoxane. U.S. Pat No. 4,659,685 (Coleman, III et al.) describes catalysts which are composed of two 20 supported catalysts (one a metallocene complex supported catalyst and the second a non-metallocene transition metal compound supported catalyst) and an aluminoxane. The disadvantages of such catalysts in the commercial manufacture of ethylene polymers are primarily twofold. Although, the choice of the metallocene and a non-metallocene transition metal compounds 25 and their ratio would lead to polymers of controlled molecular structure, the broad range of ethylene polymer structures required to meet all the commercial demands of this polymer family would require a plethora of catalyst compositions and formulations. In particular, the catalyst compositions containing aluminoxanes (which are generally required in high 30 amounts with respect to the transition metal) are unsuitable for higher temperature solution processes as such amount of the aluminum compounds result in low catalyst efficiencies and yield ethylene polymers with low molecular weights and broad molecular weight distributions.

It would be desirable to provide an economical solution 35 process which would provide ethylene interpolymers with controlled composition and molecular weight distributions. It would be additionally

desirable to provide a process for preparing such interpolymers with reduced complexity and greater flexibility in producing a full range of interpolymer compositions in a controllable fashion. It would be particularly desirable to economically produce ethylene interpolymer  
5 compositions having improved impact and tear properties, improved optical properties, high modulus and higher thermal stabilities.

We have now discovered polymerization processes for preparing interpolymer compositions of controlled composition and molecular weight  
10 distributions. The processes utilize at least one homogeneous polymerization catalyst and at least one heterogeneous polymerization catalyst in separate reactors connected in series or in parallel.

The First Process is directed to:

A process for preparing an ethylene/ $\alpha$ -olefin interpolymer  
15 composition, characterized by:

(A) reacting by contacting ethylene and at least one other  $\alpha$ -olefin under solution polymerization conditions in the presence of a homogeneous catalyst composition containing either no aluminum cocatalyst or only a small amount of aluminum cocatalyst in at least one reactor to  
20 produce a solution of a first interpolymer which has a narrow composition distribution and a narrow molecular weight distribution,

(B) reacting by contacting ethylene and at least one other  $\alpha$ -olefin under solution polymerization conditions and at a higher polymerization reaction temperature than used in step (A) in the presence  
25 of a heterogeneous Ziegler catalyst in at least one other reactor to produce a solution of a second interpolymer which has a broad composition distribution and a broad molecular weight distribution, wherein the Ziegler catalyst comprises

(i) a solid support component derived from a magnesium  
30 halide or silica, and

(ii) a transition metal component represented by the formulas:  $\text{TrX}'_4\text{-q(OR}^1\text{)}_q$ ,  $\text{TrX}'_4\text{-qR}^2_q$ ,  $\text{VOX}'_3$  and  $\text{VO (OR}^1\text{)}_3$ , wherein:

Tr is a Group IVB, VB, or VIB metal,

q is 0 or a number equal to or less than 4,

35 X' is a halogen, and

$R^1$  is an alkyl group, aryl group or cycloalkyl group having from 1 to 20 carbon atoms, and

$R^2$  is an alkyl group, aryl group, aralkyl group, or substituted aralkyl group, and

5 (C) combining the solution of the first interpolymer with the solution of the second interpolymer to form a high temperature polymer solution comprising the ethylene/a-olefin interpolymer composition, and

(D) removing the solvent from the polymer solution of step (C) and recovering the ethylene/a-olefin interpolymer composition.

10

These polymerizations are generally carried out under solution conditions to facilitate the intimate mixing of the two polymer-containing streams. The homogeneous catalyst is chosen from those metallocene-type catalysts which are capable of producing ethylene/a-olefin interpolymers of sufficiently high molecular weight under solution process polymerization conditions (e.g., temperatures greater than or equal to about 100°C). The heterogeneous catalyst is also chosen from those catalysts which are capable of efficiently producing the polymers under high temperature (e.g., temperatures greater than or equal to about 180°C) solution process conditions.

20

In addition, there is provided a second process for preparing interpolymer compositions of controlled composition and controlled molecular weight distributions.

The Second Process is directed to:

25

A process for preparing an ethylene/a-olefin interpolymer composition, characterized by:

(A) polymerizing ethylene and at least one other a-olefin in a solution process under suitable solution polymerization temperatures and pressures in at least one reactor containing a homogeneous catalyst composition containing either no aluminum cocatalyst or only a small amount of aluminum cocatalyst to produce a first interpolymer solution comprising a first interpolymer having has a narrow composition distribution and a narrow molecular weight distribution, and

30

(B) sequentially passing the interpolymer solution of (A) into at least one other reactor containing a heterogeneous Ziegler catalyst, ethylene and at least one other a-olefin under solution polymerization conditions and at a polymerization temperature higher than that used in

35

(A), to form a high temperature polymer solution comprising the ethylene/a-olefin interpolymer composition, wherein the Ziegler catalyst comprises

(i) a solid support component derived from a magnesium halide or silica, and

(ii) a transition metal component represented by the formulas:  $\text{TrX}'_4\text{-q}(\text{OR}^1)_q$ ,  $\text{TrX}'_4\text{-qR}^2_q$ ,  $\text{VOX}'_3$  and  $\text{VO}(\text{OR}^1)_3$ , wherein:

Tr is a Group IVB, VB, or VIB metal,

q is 0 or a number equal to or less than 4,

X' is a halogen, and

R<sup>1</sup> is an alkyl group, aryl group or cycloalkyl group having from 1 to 20 carbon atoms, and

R<sup>2</sup> is an alkyl group, aryl group, aralkyl group, or substituted aralkyl group, and

(C) removing the solvent from the polymer solution of step (B) and recovering the ethylene/a-olefin interpolymer composition.

In either process, the homogeneous catalyst composition preferably exhibits a high reactivity ratio and very readily incorporates higher a-olefins.

The homogeneous catalysts employed in the production of the homogeneous ethylene interpolymer are desirably derived from monocyclopentadienyl complexes of the Group IV transition metals which contain a pendant bridging group attached to the cyclopentadienyl ring which acts as a bident ligand. Complex derivatives of titanium in the +3 or +4 oxidation state are preferred.

In another aspect of this invention, there are provided novel interpolymers of ethylene and at least one a-olefin, wherein the interpolymers have controlled composition and molecular weight distributions. The interpolymers have improved mechanical, thermal and optical properties and, surprisingly, the polymer compositions obtained by the processes described herein provide superior properties to materials obtained by merely blending the solid polymers obtained from process step (A) or (B) individually, in the First Process listed above.

The novel polymer compositions of the present invention can be ethylene homopolymers or, preferably, interpolymers of ethylene with at

least one C<sub>3</sub>-C<sub>20</sub> α-olefin and/or C<sub>4</sub>-C<sub>18</sub> diolefins. Interpolymers of ethylene and 1-octene are especially preferred. The term "interpolymer" is used herein to indicate a copolymer, or a terpolymer, or the like. That is, at least one other comonomer is polymerized with ethylene to make  
5 the interpolymer.

#### Detailed Description of the Invention

The homogeneous polymers and interpolymers of the present invention are herein defined as defined in USP 3,645,992 (Elston).  
10 Accordingly, homogeneous polymers and interpolymers are those in which the comonomer is randomly distributed within a given interpolymer molecule and wherein substantially all of the interpolymer molecules have the same ethylene/comonomer ratio within that interpolymer, whereas heterogeneous interpolymers are those in which the interpolymer molecules do not have  
15 the same ethylene/comonomer ratio.

The term "narrow composition distribution" used herein describes the comonomer distribution for homogeneous interpolymers and means that the homogeneous interpolymers have only a single melting peak and essentially lack a measurable "linear" polymer fraction. The narrow  
20 composition distribution homogeneous interpolymers can also be characterized by their SCBDI (Short Chain Branch Distribution Index) or CDBI (Composition Distribution Branch Index). The SCBDI or CDBI is defined as the weight percent of the polymer molecules having a comonomer content within 50 percent of the median total molar comonomer content.  
25 The CDBI of a polymer is readily calculated from data obtained from techniques known in the art, such as, for example, temperature rising elution fractionation (abbreviated herein as "TREF") as described, for example, in Wild et al, Journal of Polymer Science, Poly. Phys. Ed., Vol. 20, p. 441 (1982), or in U.S. Patent 4,798,081. The SCBDI or CDBI for the  
30 narrow composition distribution homogeneous interpolymers and copolymers of the present invention is preferably greater than 30 percent, especially greater than 50 percent. The narrow composition distribution homogeneous interpolymers and copolymers used in this invention essentially lack a measurable "high density" (i.e., "linear" or homopolymer) fraction as  
35 measured by the TREF technique. The homogeneous interpolymers and polymers have a degree of branching less than or equal to 2 methyls/1000



carbons in 15 percent (by weight) or less, preferably less than 10 percent (by weight), and especially less than 5 percent (by weight).

The term "broad composition distribution" used herein describes the comonomer distribution for heterogeneous interpolymers and means that the heterogeneous interpolymers have a "linear" fraction and that the heterogeneous interpolymers have multiple melting peaks (i.e., exhibit at least two distinct melting peaks). The heterogeneous interpolymers and polymers have a degree of branching less than or equal to 2 methyls/1000 carbons in 10 percent (by weight) or more, preferably more than 15 percent (by weight), and especially more than 20 percent (by weight). The heterogeneous interpolymers also have a degree of branching equal to or greater than 25 methyls/1000 carbons in 25 percent or less (by weight), preferably less than 15 percent (by weight), and especially less than 10 percent (by weight).

The homogeneous polymers and interpolymers used to make the novel polymer compositions of the present invention can be ethylene homopolymers or, preferably, interpolymers of ethylene with at least one C<sub>3</sub>-C<sub>20</sub> α-olefin and/or C<sub>4</sub>-C<sub>18</sub> diolefins. Homogeneous copolymers of ethylene and propylene, butene-1, hexene-1, 4-methyl-1-pentene and octene-1 are preferred and copolymers of ethylene and 1-octene are especially preferred.

Either, or both, of the homogeneous ethylene polymer and the heterogeneous ethylene polymer can be an ethylene homopolymer. Preferably, however, either the homogeneous ethylene polymer or the heterogeneous ethylene polymer is an ethylene/α-olefin interpolymer. Ethylene polymer compositions wherein both the homogeneous ethylene polymer and the heterogeneous ethylene polymer are ethylene/α-olefin interpolymers are especially preferred.

The homogeneous ethylene polymer and the heterogeneous ethylene polymer used in the compositions described herein can each be made separately in different reactors, and subsequently blended together to make the interpolymer compositions of the present invention. Preferably, though, the homogeneous ethylene polymer and the heterogeneous ethylene polymer used in the compositions described herein are made in a multiple reactor scheme, operated either in parallel or in series. In the multiple reactor scheme, at least one of the reactors makes the

homogeneous ethylene polymer and at least one of the reactors makes the heterogeneous ethylene polymer. In a preferred mode of operation, the reactors are operated in a series configuration to make most advantage of the high polymerization temperatures allowed by the heterogeneous catalyst. When the reactors are connected in series, the polymerization reaction product from step (A) is fed directly (i.e., sequentially) into the reactor(s) for step (B) along with the ethylene/ $\alpha$ -olefin reactants and heterogeneous catalyst and solvent.

Other unsaturated monomers usefully polymerized according to the present invention include, for example, ethylenically unsaturated monomers, conjugated or nonconjugated dienes, polyenes, etc. Preferred monomers include the  $C_2$ - $C_{10}$   $\alpha$ -olefins especially ethylene, 1-propene, 1-butene, 1-hexene, 4-methyl-1-pentene, and 1-octene. Other preferred monomers include styrene, halo- or alkyl substituted styrenes, vinylbenzocyclobutane, 1,4-hexadiene, cyclopentene, cyclohexene and cyclooctene.

The density of the ethylene polymer compositions for use in the present invention is measured in accordance with ASTM D-792 and is generally from  $0.87 \text{ g/cm}^3$  to  $0.965 \text{ g/cm}^3$ , preferably from  $0.88 \text{ g/cm}^3$  to  $0.95 \text{ g/cm}^3$ , and especially from  $0.9 \text{ g/cm}^3$  to  $0.935 \text{ g/cm}^3$ . The density of the homogeneous ethylene polymer used to make the ethylene polymer compositions is generally from  $0.865 \text{ g/cm}^3$  to  $0.92 \text{ g/cm}^3$ , preferably from  $0.88 \text{ g/cm}^3$  to  $0.915 \text{ g/cm}^3$ , and especially from  $0.89 \text{ g/cm}^3$  to  $0.91 \text{ g/cm}^3$ . The density of the heterogeneous ethylene polymer used to make the ethylene polymer compositions is generally from  $0.9 \text{ g/cm}^3$  to  $0.965 \text{ g/cm}^3$ , preferably from  $0.9 \text{ g/cm}^3$  to  $0.95 \text{ g/cm}^3$ , and especially from  $0.915 \text{ g/cm}^3$  to  $0.935 \text{ g/cm}^3$ .

Generally, the amount of the ethylene polymer produced using the homogeneous catalyst and incorporated into the ethylene polymer composition is from 15 percent to 85 percent, by weight of the composition, preferably 25 percent to 75 percent, by weight of the composition.

The molecular weight of the ethylene polymer compositions for use in the present invention is conveniently indicated using a melt index measurement according to ASTM D-1238, Condition 190 C/2.16 kg (formally known as "Condition (E)" and also known as  $I_2$ ). Melt index is inversely

proportional to the molecular weight of the polymer. Thus, the higher the molecular weight, the lower the melt index, although the relationship is not linear. The melt index for the ethylene polymer compositions used herein is generally from 0.1 grams/10 minutes (g/10 min) to 100 g/10 min, preferably from 0.3 g/10 min to 30 g/10 min, and especially from 0.5 g/10 min to 10 g/10 min.

Additives such as antioxidants (e.g., hindered phenolics (e.g., Irganox® 1010 made by Ciba Geigy Corp.), phosphites (e.g., Irgafos® 168 also made by Ciba Geigy Corp.)), cling additives (e.g., polyisobutylene (PIB)), antiblock additives, pigments, and the like can also be included in the polyethylene compositions, to the extent that they do not interfere with the enhanced composition properties discovered by Applicants.


#### 15 The Homogeneous Catalysts

The homogeneous catalysts used in the invention are based on those monocyclopentadienyl transition metal complexes described in the art as constrained geometry metal complexes. These catalysts are highly efficient, meaning that they are efficient enough such that the catalyst residues left in the polymer do not influence the polymer quality. Typically, less than or equal to 10 ppm of the metal atom (designated herein as "M") is detectable and, when using the appropriate cocatalyst (e.g., one of the aluminoxanes described herein) the detectable aluminum residue is less than or equal to 250 ppm. Suitable constrained geometry catalysts for use herein preferably include constrained geometry catalysts as disclosed in European patent publication 416,815. The monocyclopentadienyl transition metal olefin polymerization catalysts taught in USP 5,026,798 (Canich) are also suitable for use in preparing the polymers of the present invention.

30 The foregoing catalysts may be further described as comprising a metal coordination complex comprising a metal of group 4 of the Periodic Table of the Elements and a delocalized  $\pi$ -bonded moiety substituted with a constrain-inducing moiety, said complex having a constrained geometry about the metal atom such that the angle at the metal between the centroid of the delocalized, substituted  $\pi$ -bonded moiety and the center of at least one remaining substituent is less than such angle in a similar complex

containing a similar  $\pi$ -bonded moiety lacking in such constrain-inducing substituent, and provided further that for such complexes comprising more than one delocalized, substituted  $\pi$ -bonded moiety, only one thereof for each metal atom of the complex is a cyclic, delocalized, substituted  $\pi$ -bonded moiety. The catalyst further comprises an activating cocatalyst.

Preferred catalyst complexes correspond to the formula:



wherein:

10

M is a metal of group 4 of the Periodic Table of the Elements;

Cp\* is a cyclopentadienyl or substituted cyclopentadienyl group bound in an  $h^5$  bonding mode to M;

15

Z is a moiety comprising boron, or a member of group 14 of the Periodic Table of the Elements, and optionally sulfur or oxygen, said moiety having up to 20 non-hydrogen atoms, and optionally Cp\* and Z together form a fused ring system;

20


X independently each occurrence is an anionic ligand group having up to 30 non-hydrogen atoms;

25

n is 1 or 2; and.

Y is an anionic or nonanionic ligand group bonded to Z and M comprising nitrogen, phosphorus, oxygen or sulfur and having up to 20 non-hydrogen atoms, optionally Y and Z together form a fused ring system.

5 More preferably still, such complexes correspond to the formula:



10 wherein:

R' each occurrence is independently selected from the group consisting of hydrogen, alkyl, aryl, and silyl, and combinations thereof having up to 20 non-hydrogen atoms;

15 X each occurrence independently is selected from the group consisting of hydride, halo, alkyl, aryl, silyl, aryloxy, alkoxy, amide, siloxy and combinations thereof having up to 20 non-hydrogen atoms;


Y is -O-, -S-, -NR\*- , -PR\*- , or a neutral two electron donor  
20 ligand selected from the group consisting of OR\*, SR\*, NR\*<sub>2</sub> or PR\*<sub>2</sub>;

M is as previously defined; and

Z is SiR\*<sub>2</sub>, CR\*<sub>2</sub>, SiR\*<sub>2</sub>SiR\*<sub>2</sub>, CR\*<sub>2</sub>CR\*<sub>2</sub>, CR\*=CR\*, CR\*<sub>2</sub>SiR\*<sub>2</sub>,  
25 BR\*; wherein

R\* each occurrence is independently selected from the group consisting of hydrogen, alkyl, aryl, silyl groups having up to 20 non-hydrogen atoms, and mixtures thereof, or two or more R\* groups from Y, Z,  
30 or both Y and Z form a fused ring system; and n is 1 or 2.

Most highly preferred complex compounds are amidosilane- or amidoalkanediyl- compounds corresponding to the formula:



5 wherein:

M is titanium, zirconium or hafnium, bound in an  $h^5$  bonding mode to the cyclopentadienyl group;

10

R' each occurrence is independently selected from the group consisting of hydrogen, alkyl and aryl and combinations thereof having up to 7 carbon atoms, or silyl;

15

E is silicon or carbon;

X independently each occurrence is hydride, halo, alkyl, aryl, aryloxy or alkoxy of up to 10 carbons, or silyl;

20

m is 1 or 2; and

n is 1 or 2.

25


Examples of the above most highly preferred metal coordination compounds include compounds wherein the R' on the amido group is methyl, ethyl, propyl, butyl, pentyl, hexyl, (including isomers), norbornyl, benzyl, phenyl, etc.; the cyclopentadienyl group is cyclopentadienyl,

indenyl, tetrahydroindenyl, fluorenyl, octahydrofluorenyl, etc.; R' on the foregoing cyclopentadienyl groups each occurrence is hydrogen, methyl, ethyl, propyl, butyl, pentyl, hexyl, (including isomers), norbornyl, benzyl, phenyl, etc.; and X is chloro, bromo, iodo, methyl, ethyl, propyl, butyl, pentyl, hexyl, (including isomers), norbornyl, benzyl, phenyl, etc.

Specific compounds include: (tert-butylamido)(tetramethyl-h<sup>5</sup>-cyclopentadienyl)-1,2-ethanediylzirconium dichloride, (tert-butylamido)(tetramethyl-h<sup>5</sup>-cyclopentadienyl)-1,2-ethanediyltitanium dichloride, (methylamido)(tetramethyl-h<sup>5</sup>-cyclopentadienyl)-1,2-ethanediylzirconium dichloride, (methylamido)(tetramethyl-h<sup>5</sup>-cyclopentadienyl)-1,2-ethanediyltitanium dichloride, (ethylamido)(tetramethyl-h<sup>5</sup>-cyclopentadienyl)methylenetitanium dichloride, (tertbutylamido)dibenzyl(tetramethyl-h<sup>5</sup>-cyclopentadienyl)silanezirconium dibenzyl, (benzylamido)dimethyl-(tetramethyl-h<sup>5</sup>-cyclopentadienyl)silanezirconium dichloride, (phenylphosphido)dimethyl(tetramethyl-h<sup>5</sup>-cyclopentadienyl)silanezirconium dibenzyl, (tertbutylamido)dimethyl(tetramethyl-h<sup>5</sup>-cyclopentadienyl)silanezirconium dimethyl, and the like.

The catalyst compositions are derived from reacting the metal complex compounds with a suitable activating agent or cocatalyst or combination of cocatalysts. Suitable cocatalysts for use herein include polymeric or oligomeric aluminoxanes, especially aluminoxanes soluble in non-aromatic hydrocarbon solvent, as well as inert, compatible, noncoordinating, ion forming compounds; or combinations of polymeric/oligomeric aluminoxanes and inert, compatible, noncoordinating, ion forming compounds. Preferred cocatalysts contain inert, noncoordinating, boron compounds.

Ionic active catalyst species which can be used to polymerize the polymers described herein correspond to the formula:



5

wherein:

10

M is a metal of group 4 of the Periodic Table of the Elements;

Cp\* is a cyclopentadienyl or substituted cyclopentadienyl group bound in an  $h^5$  bonding mode to M;

15

Z is a moiety comprising boron, or a member of group 14 of the Periodic Table of the Elements, and optionally sulfur or oxygen, said moiety having up to 20 non-hydrogen atoms, and optionally Cp\* and Z together form a fused ring system;

20

X independently each occurrence is an anionic ligand group having up to 30 non-hydrogen atoms;

25

n is 1 or 2; and

A<sup>-</sup> is a noncoordinating, compatible anion.

One method of making the ionic catalyst species which can be utilized to make the polymers of the present invention involve combining:



a) at least one first component which is a mono(cyclopentadienyl) derivative of a metal of Group 4 of the Periodic Table of the Elements as described previously containing at least one substituent which will combine with the cation of a second component  
5 (described hereinafter) which first component is capable of forming a cation formally having a coordination number that is one less than its valence, and

b) at least one second component which is a salt of a Bronsted acid and a noncoordinating, compatible anion.

10 Compounds useful as a second component in the preparation of the ionic catalysts useful in this invention can comprise a cation, which is a Bronsted acid capable of donating a proton, and a compatible noncoordinating anion. Preferred anions are those containing a single coordination complex comprising a charge-bearing metal or metalloid core  
15 which anion is relatively large (bulky), capable of stabilizing the active catalyst species (the Group 4 cation) which is formed when the two components are combined and sufficiently labile to be displaced by olefinic, diolefinic and acetylenically unsaturated substrates or other neutral Lewis bases such as ethers, nitriles and the like. Compounds  
20 containing anions which comprise coordination complexes containing a single metal or metalloid atom are, of course, well known and many, particularly such compounds containing a single boron atom in the anion portion, are available commercially. In light of this, salts containing anions comprising a coordination complex containing a single boron atom  
25 are preferred.

Highly preferably, the second component useful in the preparation of the catalysts of this invention may be represented by the following general formula:



wherein:

L is a neutral Lewis base;

(L-H)<sup>+</sup> is a Bronsted acid; and

35 [A]<sup>-</sup> is a compatible, noncoordinating anion.

More preferably  $[\Lambda]^-$  corresponds to the formula:




5 wherein:

B is boron in a valence state of 3; and

Q independently each occurrence is selected from the Group consisting of hydride, dialkylamido, halide, alkoxide, aryloxy, hydrocarbyl, and substituted-hydrocarbyl radicals of up to 20 carbons with  
10 the proviso that in not more than one occurrence is Q halide.

Illustrative, but not limiting, examples of boron compounds which may be used as a second component in the preparation of the improved catalysts of this invention are trialkyl-substituted ammonium salts such as triethylammonium tetraphenylborate, tripropylammonium  
15 tetraphenylborate, tris(n-butyl)ammonium tetraphenylborate, trimethylammonium tetrakis(p-tolyl)borate, tributylammonium tetrakis(pentafluorophenyl)borate, tripropylammonium tetrakis(2,4-dimethylphenyl)borate, tributylammonium tetrakis(3,5-dimethylphenyl)borate, triethylammonium tetrakis(3,5-di-  
20 trifluoromethylphenyl)borate and the like. Also suitable are N,N-dialkylanilinium salts such as N,N-dimethylanilinium tetraphenylborate, N,N-diethylanilinium tetraphenylborate, N,N,2,4,6-pentamethylanilinium tetraphenylborate and the like; dialkylammonium salts such as di(i-propyl)ammonium tetrakis(pentafluorophenyl)borate, dicyclohexylammonium  
25 tetraphenylborate and the like; and triarylphosphonium salts such as triphenylphosphonium tetraphenylborate, tris(methylphenyl)phosphonium tetrakis(pentafluorophenyl)borate, tris(dimethylphenyl)phosphonium tetraphenylborate and the like.

Preferred ionic catalysts are those having a limiting charge separated structure corresponding to the formula:



wherein:

5

M is a metal of group 4 of the Periodic Table of the Elements;

Cp\* is a cyclopentadienyl or substituted cyclopentadienyl  
 10 group bound in an  $h^5$  bonding mode to M;

Z is a moiety comprising boron, or a member of group 14 of the  
 Periodic Table of the Elements, and optionally sulfur or oxygen, said  
 moiety having up to 20 non-hydrogen atoms, and optionally Cp\* and Z  
 15 together form a fused ring system;


X independently each occurrence is an anionic ligand group  
 having up to 30 non-hydrogen atoms;

20

n is 1 or 2; and

XA\*<sup>-</sup> is <sup>-</sup>X(B(C<sub>6</sub>F<sub>5</sub>)<sub>3</sub>).

This class of cationic complexes can also be conveniently prepared by contacting a metal compound corresponding to the formula:




wherein:

5 Cp\*, M, and n are as previously defined,  
with tris(pentafluorophenyl)borane cocatalyst under conditions to cause abstraction of X and formation of the anion  $\text{X}(\text{B}(\text{C}_6\text{F}_5)_3)$ .

Preferably X in the foregoing ionic catalyst is  
C<sub>1</sub>-C<sub>10</sub> hydrocarbyl, most preferably methyl or benzyl.

10 The preceding formula is referred to as the limiting, charge separated structure. However, it is to be understood that, particularly in solid form, the catalyst may not be fully charge separated. That is, the X group may retain a partial covalent bond to the metal atom, M. Thus, the catalysts may be alternately depicted as possessing the formula:



15

The catalysts are preferably prepared by contacting the derivative of a Group 4 metal with the tris(pentafluorophenyl)borane in an inert diluent such as an organic liquid. Tris(pentafluorophenyl)borane is a commonly available Lewis acid that may be readily prepared according to known techniques. The compound is disclosed in Marks, et al. J. Am. Chem. Soc. 1991, 113, 3623-3625 for use in alkyl abstraction of zirconocenes.

The homogeneous catalyst can contain either no aluminum  
25 cocatalyst or only a small amount (i.e., from 3:1 Al:M ratio to 100:1 Al:M

ratio) of aluminum cocatalyst. For example, the cationic complexes used as homogeneous catalysts may be further activated by the use of an additional activator such as an alkylaluminumoxane. Preferred co-activators include methylaluminumoxane, propylaluminumoxane, isobutylaluminumoxane, combinations thereof and the like. So-called modified methylaluminumoxane (MMAO) is also suitable for use as a cocatalyst. One technique for preparing such modified aluminumoxane is disclosed in U.S. Patent 4,960,878 (Crapo et al.). Aluminumoxanes can also be made as disclosed in U.S. Patents Nos. 4,544,762 (Kaminsky et al.) ; 5,015,749 (Schmidt et al.); 5,041,583 (Sangokoya); 5,041,584 (Crapo et al.); and 5,041,585 (Deavenport et al.).

The homogeneous catalysts useful for the production of the ethylene interpolymers of narrow composition and molecular weight distribution may also be supported on an inert support. Typically, the support can be any solid, particularly porous supports such as talc or inorganic oxides, or resinous support materials such as a polyolefin. Preferably, the support material is an inorganic oxide in finely divided form.

Suitable inorganic oxide materials which are desirably employed in accordance with this invention include Group IIA, IIIA, IVA, or IVB metal oxides such as silica, alumina, and silica-alumina and mixtures thereof. Other inorganic oxides that may be employed either alone or in combination with the silica, alumina or silica-alumina are magnesia, titania, zirconia, and the like. Other suitable support materials, however, can be employed, for example, finely divided polyolefins such as finely divided polyethylene.

The metal oxides generally contain acidic surface hydroxyl groups which will react with the homogeneous catalyst component added to the reaction slurry. Prior to use, the inorganic oxide support is dehydrated, i.e., subjected to a thermal treatment in order to remove water and reduce the concentration of the surface hydroxyl groups. The treatment is carried out in vacuum or while purging with a dry inert gas such as nitrogen at a temperature of 100°C to 1000°C, and preferably, from 300°C to 800°C. Pressure considerations are not critical. The duration of the thermal treatment can be from 1 to 24 hours; however, shorter or

longer times can be employed provided equilibrium is established with the surface hydroxyl groups.

#### The Heterogeneous Catalysts

5                   The heterogeneous catalysts suitable for use in the invention are typical supported, Ziegler-type catalysts which are particularly useful at the high polymerization temperatures of the solution process. Examples of such compositions are those derived from organomagnesium compounds, alkyl halides or aluminum halides or hydrogen chloride, and a  
10 transition metal compound. Examples of such catalysts are described in U.S. Pat Nos. 4,314,912 (Lowery, Jr. et al.), 4,547,475 (Glass et al.), and 4,612,300 (Coleman, III).

                  Particularly suitable organomagnesium compounds include, for example, hydrocarbon soluble dihydrocarbylmagnesium such as the magnesium  
15 dialkyls and the magnesium diaryls. Exemplary suitable magnesium dialkyls include particularly n-butyl-sec-butylmagnesium, diisopropylmagnesium, di-n-hexylmagnesium, isopropyl-n-butyl-magnesium, ethyl-n-hexylmagnesium, ethyl-n-butylmagnesium, di-n-octylmagnesium and others wherein the alkyl has from 1 to 20 carbon atoms. Exemplary suitable magnesium diaryls  
20 include diphenylmagnesium, dibenzylmagnesium and ditolylmagnesium. Suitable organomagnesium compounds include alkyl and aryl magnesium alkoxides and aryloxides and aryl and alkyl magnesium halides with the halogen-free organomagnesium compounds being more desirable.

                  Among the halide sources which can be employed herein are the  
25 active non-metallic halides, metallic halides, and hydrogen chloride.

                  Suitable non-metallic halides are represented by the formula  $R'X$  wherein  $R'$  is hydrogen or an active monovalent organic radical and  $X$  is a halogen. Particularly suitable non-metallic halides include, for example, hydrogen halides and active organic halides such as t-alkyl  
30 halides, allyl halides, benzyl halides and other active hydrocarbyl halides wherein hydrocarbyl is as defined hereinbefore. By an active organic halide is meant a hydrocarbyl halide that contains a labile halogen at least as active, i.e., as easily lost to another compound, as the halogen of sec-butyl chloride, preferably as active as t-butyl  
35 chloride. In addition to the organic monohalides, it is understood that organic dihalides, trihalides and other polyhalides that are active as

defined hereinbefore are also suitably employed. Examples of preferred active non-metallic halides include hydrogen chloride, hydrogen bromide, t-butyl chloride, t-amyl bromide, allyl chloride, benzyl chloride, crotyl chloride, methylvinyl carbonyl chloride,  $\alpha$ -phenylethyl bromide, diphenyl  
5 methyl chloride and the like. Most preferred are hydrogen chloride, t-butyl chloride, allyl chloride and benzyl chloride.

Suitable metallic halides which can be employed herein include those represented by the formula  $MR_y-aX_a$  wherein:

M is a metal of Groups IIB, IIIA or IVA of Mendeleev's  
10 Periodic Table of Elements,  
R is a monovalent organic radical,  
X is a halogen,  
Y has a value corresponding to the valence of M, and  
a has a value from 1 to y.

15

Preferred metallic halides are aluminum halides of the formula  $AlR_3-aX_a$  wherein:

each R is independently hydrocarbyl as hereinbefore defined  
such as alkyl,  
20 X is a halogen and  
a is a number from 1 to 3.

Most preferred are alkylaluminum halides such as ethylaluminum sesquichloride, diethylaluminum chloride, ethylaluminum dichloride, and  
25 diethylaluminum bromide, with ethylaluminum dichloride being especially preferred. Alternatively, a metal halide such as aluminum trichloride or a combination of aluminum trichloride with an alkyl aluminum halide or a trialkyl aluminum compound may be suitably employed.

It is understood that the organic moieties of the  
30 aforementioned organomagnesium, e.g.,  $R''$ , and the organic moieties of the halide source, e.g., R and  $R'$ , are suitably any other organic radical provided that they do not contain functional groups that poison conventional Ziegler catalysts.

The magnesium halide can be preformed from the organomagnesium  
35 compound and the halide source or it can be formed in situ in which instance the catalyst is preferably prepared by mixing in a suitable

solvent or reaction medium (1) the organomagnesium component and (2) the halide source, followed by the other catalyst components.

Any of the conventional Ziegler-Natta transition metal compounds can be usefully employed as the transition metal component in preparing the supported catalyst component. Typically, the transition metal component is a compound of a Group IVB, VB, or VIB metal. The transition metal component is generally, represented by the formulas:  
5  $\text{TrX}'_4\text{-q}(\text{OR}^1)_q$ ,  $\text{TrX}'_4\text{-qR}^2_q$ ,  $\text{VOX}'_3$  and  $\text{VO}(\text{OR}^1)_3$ .

Tr is a Group IVB, VB, or VIB metal, preferably a Group IVB or  
10 VB metal, preferably titanium, vanadium or zirconium,

q is 0 or a number equal to or less than 4,

X' is a halogen, and

R<sup>1</sup> is an alkyl group, aryl group or cycloalkyl group having  
from 1 to 20 carbon atoms, and

15 R<sup>2</sup> is an alkyl group, aryl group, aralkyl group, substituted aralkyls, and the like. The aryl, aralkyls and substituted aralkyls contain 1 to 20 carbon atoms, preferably 1 to 10 carbon atoms. When the transition metal compound contains a hydrocarbyl group, R<sup>2</sup>, being an alkyl, cycloalkyl, aryl, or aralkyl group, the hydrocarbyl group will  
20 preferably not contain an H atom in the position beta to the metal carbon bond. Illustrative but non-limiting examples of aralkyl groups are methyl, neo-pentyl, 2,2-dimethylbutyl, 2,2-dimethylhexyl; aryl groups such as benzyl; cycloalkyl groups such as 1-norbornyl. Mixtures of these transition metal compounds can be employed if desired.

25 Illustrative examples of the transition metal compounds include  $\text{TiCl}_4$ ,  $\text{TiBr}_4$ ,  $\text{Ti}(\text{OC}_2\text{H}_5)_3\text{Cl}$ ,  $\text{Ti}(\text{OC}_2\text{H}_5)\text{Cl}_3$ ,  $\text{Ti}(\text{OC}_4\text{H}_9)_3\text{Cl}$ ,  $\text{Ti}(\text{OC}_3\text{H}_7)_2\text{Cl}_2$ ,  $\text{Ti}(\text{OC}_6\text{H}_{13})_2\text{Cl}_2$ ,  $\text{Ti}(\text{OC}_8\text{H}_{17})_2\text{Br}_2$ , and  $\text{Ti}(\text{OC}_{12}\text{H}_{25})\text{Cl}_3$ ,  $\text{Ti}(\text{O-i-C}_3\text{H}_7)_4$ , and  $\text{Ti}(\text{O-n-C}_4\text{H}_9)_4$ .

30 Illustrative examples of vanadium compounds include  $\text{VCl}_4$ ,  $\text{VOCl}_3$ ,  $\text{VO}(\text{OC}_2\text{H}_5)_3$ , and  $\text{VO}(\text{OC}_4\text{H}_9)_3$ .

Illustrative examples of zirconium compounds include  $\text{ZrCl}_4$ ,  $\text{ZrCl}_3(\text{OC}_2\text{H}_5)$ ,  $\text{ZrCl}_2(\text{OC}_2\text{H}_5)_2$ ,  $\text{ZrCl}(\text{OC}_2\text{H}_5)_3$ ,  $\text{Zr}(\text{OC}_2\text{H}_5)_4$ ,  $\text{ZrCl}_3(\text{OC}_4\text{H}_9)$ ,  $\text{ZrCl}_2(\text{OC}_4\text{H}_9)_2$ , and  $\text{ZrCl}(\text{OC}_4\text{H}_9)_3$ .

As indicated above, mixtures of the transition metal compounds  
35 may be usefully employed, no restriction being imposed on the number of transition metal compounds which may be contracted with the support. Any



halogenide and alkoxide transition metal compound or mixtures thereof can be usefully employed. The previously named transition metal compounds are especially preferred with vanadium tetrachloride, vanadium oxychloride, titanium tetraisopropoxide, titanium tetrabutoxide, and titanium tetrachloride being most preferred.

Suitable catalyst materials may also be derived from a inert oxide supports and transition metal compounds. Examples of such compositions suitable for use in the solution polymerization process are described in U. S. Patent No. 5,231,151.

The inorganic oxide support used in the preparation of the catalyst may be any particulate oxide or mixed oxide as previously described which has been thermally or chemically dehydrated such that it is substantially free of adsorbed moisture.

The specific particle size, surface area, pore volume, and number of surface hydroxyl groups characteristic of the inorganic oxide are not critical to its utility in the practice of the invention. However, since such characteristics determine the amount of inorganic oxide to be employed in preparing the catalyst compositions, as well as affecting the properties of polymers formed with the aid of the catalyst compositions, these characteristics must frequently be taken into consideration in choosing an inorganic oxide for use in a particular aspect of the invention. In general, optimum results are usually obtained by the use of inorganic oxides having an average particle size in the range of 1 to 100 microns, preferably 2 to 20 microns; a surface area of 50 to 1,000 square meters per gram, preferably 100 to 400 square meters per gram; and a pore volume of 0.5 to 3.5 cm<sup>3</sup> per gram; preferably 0.5 to 2 cm<sup>3</sup> per gram.

In order to further improve catalyst performance, surface modification of the support material may be desired. Surface modification is accomplished by specifically treating the support material such as silica, alumina or silica-alumina with an organometallic compound having hydrolytic character. More particularly, the surface modifying agents for the support materials comprise the organometallic compounds of the metals of Group IIA and IIIA of the Periodic Table. Most preferably the organometallic compounds are selected from magnesium and aluminum organometallics and especially from magnesium and aluminum alkyls or

mixtures thereof represented by the formulas and  $R^1MgR^2$  and  $R^1R^2AlR^3$  wherein each of  $R^1$ ,  $R^2$  and  $R^3$  which may be the same or different are alkyl groups, aryl groups, cycloalkyl groups, aralkyl groups, alkoxide groups, alkadienyl groups or alkenyl groups. The hydrocarbon groups  $R^1$ ,  $R^2$  and  $R^3$  can contain between 1 and 20 carbon atoms and preferably from 1 to about 10 carbon atoms.

The surface modifying action is effected by adding the organometallic compound in a suitable solvent to a slurry of the support material. Contact of the organometallic compound in a suitable solvent and the support is maintained from 30 to 180 minutes and preferably from 60 to 90 minutes at a temperature in the range of 20° to 100° C. The diluent employed in slurrying the support can be any of the solvents employed in solubilizing the organometallic compound and is preferably the same.

In order to more readily produce interpolymer compositions of controlled composition and molecular weight distribution, the constrained-geometry component catalyst and the Ziegler-type transition metal catalyst component should have different reactivity ratios. The reactivity ratio of the homogeneous catalyst may be higher than the reactivity ratio of the heterogeneous catalyst. In such instances, the contribution of the narrow composition and molecular weight distribution polymer molecules, formed in the first reactor, to the whole interpolymer product would yield improvements in thermal resistance and crystallization behavior of the resin. Preferably, but not limiting, the reactivity ratio of the homogeneous catalyst introduced into the first reactor should be lower than the reactivity ratio of the heterogeneous catalyst in order to have the most benefit of a simplified process and to produce interpolymers of the most suitable compositions.

The reactivity ratios of the metallocenes and transition metal components in general are obtained by methods well known such as, for example, as described in "Linear Method for Determining Monomer Reactivity Ratios in Copolymerization", M. Fineman and S. D. Ross, J. Polymer Science 5, 259 (1950) or "Copolymerization", F. R. Mayo and C. Walling, Chem. Rev. 46, 191 (1950).

35

For example, to determine reactivity ratios, the most widely used copolymerization model is based on the following equations:



5



10



here  $M_1$ ,  $M_2$  refer to monomer molecules and  $M_1^*$  or  $M_2^*$  refer to a growing polymer chain to which monomer  $M_1$  or  $M_2$  has most recently attached.  $M_1$  is typically ethylene;  $M_2$  is typically an  $\alpha$ -olefin comonomer.

The  $k_{ij}$  values are the rate constants for the indicated reactions. In this case,  $k_{11}$  represents the rate at which an ethylene unit inserts into a growing polymer chain in which the previously inserted monomer unit was also ethylene. The reactivity ratios follow as:  
 $r_1 = k_{11}/k_{12}$  and  $r_2 = k_{22}/k_{21}$  wherein  $k_{11}$ ,  $k_{12}$ ,  $k_{22}$ , and  $k_{21}$  are the rate constants for ethylene (1) or comonomer (2) addition to a catalyst site where the last polymerized monomer is ethylene ( $k_{1X}$ ) or comonomer (2) ( $k_{2X}$ ). A lower value of  $r_1$  for a particular catalyst translates into the formation of an interpolymer of higher comonomer content produced in a fixed reaction environment. In a preferred embodiment of the invention, the reactivity ratio,  $r_1$ , of the homogeneous catalyst is less than half that of the heterogeneous catalyst.

Therefore, in the desirable practice of the invention, the homogeneous catalyst produces a polymer of higher comonomer content than that of the polymer produced by the heterogeneous in a reaction environment which is low in the concentration of the comonomer. As the contents of the first reactor enter a second reactor, the concentration of the comonomer in the second reactor is reduced. Hence, the reaction environment in which the heterogeneous catalyst forms polymer is such that a polymer containing a lower comonomer content is produced. Under such reaction conditions, the polymer so formed will have a well-defined and

narrow composition distribution and narrow molecular weight distribution. The resulting whole interpolymer product can be readily controlled by choice of catalysts, comonomers, and reaction temperatures in an economical and reproducible fashion. In addition, simple changes in  
5 monomer concentrations and conversions in each reactor allows the manufacture of a broad range of interpolymer products.

The heterogeneous polymers and interpolymers used to make the novel polymer compositions of the present invention can be ethylene homopolymers or, preferably, interpolymers of ethylene with at least one  
10 C<sub>3</sub>-C<sub>20</sub>  $\alpha$ -olefin and/or C<sub>4</sub>-C<sub>18</sub> diolefins. Heterogeneous copolymers of ethylene and 1-octene are especially preferred.

#### Polymerization

The polymerization conditions for manufacturing the polymers  
15 of the present invention are generally those useful in the solution polymerization process, although the application of the present invention is not limited thereto. Slurry and gas phase polymerization processes are also believed to be useful, provided the proper catalysts and polymerization conditions are employed.

20 Multiple reactor polymerization processes are particularly useful in the present invention, such as those disclosed in USP 3,914,342 (Mitchell). The multiple reactors can be operated in series or in parallel, with at least one constrained geometry catalyst employed in one of the reactors and at least one heterogeneous catalyst employed in at  
25 least one other reactor. Preferably, the polymerization temperature of the constrained geometry portion of the polymerization is lower than that of the heterogeneous polymerization portion of the reaction.

According to one embodiment of the present process, the polymers are produced in a continuous process, as opposed to a batch  
30 process. Preferably, the polymerization temperature is from 20°C to 250°C, using constrained geometry catalyst technology. In the generally preferred embodiments where a narrow molecular weight distribution polymer ( $M_w/M_n$  of from 1.5 to 2.5) having a higher I<sub>10</sub>/I<sub>2</sub> ratio (e.g., I<sub>10</sub>/I<sub>2</sub> of at least 7, preferably at least 8, especially at least 9) is desired, the  
35 ethylene concentration in the reactor is preferably not more than 8 percent by weight of the reactor contents, especially not more than 4

percent by weight of the reactor contents. Preferably, the polymerization is performed in a solution polymerization process. Generally, manipulation of  $I_{10}/I_2$  while holding  $M_w/M_n$  relatively low for producing the polymers described herein is a function of reactor temperature and/or  
5 ethylene concentration. Reduced ethylene concentration and higher temperature generally produce higher  $I_{10}/I_2$  materials.

Separation of the interpolymer compositions from the high temperature polymer solution can be accomplished by use of devolatilizing apparatus known to those skilled in the art. Examples include USP  
10 5,084,134 (Mattiussi et al.), USP 3,014,702 (Oldershaw et al.), USP 4,808,262 (Aneja et al.), USP 4,564,063 (Tollar), USP 4,421,162 (Tollar) or USP 3,239,197 (Tollar).

#### Molecular Weight Distribution Determination

15 The interpolymer product samples analyzed by gel permeation chromatography (GPC) on a Waters 150C high temperature chromatographic unit equipped with three mixed porosity columns (Polymer Laboratories  $10^3$ ,  $10^4$ ,  $10^5$ , and  $10^6$ ), operating at a system temperature of  $140^\circ\text{C}$ . The solvent is 1,2,4-trichlorobenzene, from which 0.3 percent by weight  
20 solutions of the samples are prepared for injection. The flow rate is 1.0 milliliters/minute and the injection size is 200 microliters.

The molecular weight determination is deduced by using narrow molecular weight distribution polystyrene standards (from Polymer Laboratories) in conjunction with their elution volumes. The equivalent  
25 polyethylene molecular weights are determined by using appropriate Mark-Houwink coefficients for polyethylene and polystyrene (as described by Williams and Word in Journal of Polymer Science, Polymer Letters, Vol. 6, (621) 1968) to derive the following equation:

30 
$$M_{\text{polyethylene}} = a * (M_{\text{polystyrene}})^b.$$

In this equation,  $a = 0.4316$  and  $b = 1.0$ . Weight average molecular weight,  $M_w$ , is calculated in the usual manner according to the following formula:  $M_w = \sum w_i * M_i$ , where  $w_i$  and  $M_i$  are the weight fraction and  
35 molecular weight, respectively, of the  $i$ th fraction eluting from the GPC column.

For the interpolymer fractions and whole interpolymers described herein, the term "narrow molecular weight distribution" means that the  $M_w/M_n$  of the interpolymer (or fraction) is less than 3, preferably from 2 to 3. The  $M_w/M_n$  of the "narrow molecular weight distribution" interpolymer (or fraction) can also be described by the following equation:  $(M_w/M_n) \leq (I_{10}/I_2) - 4.63$ .

For the interpolymer fractions and whole interpolymers described herein, the term "broad molecular weight distribution" means that the  $M_w/M_n$  of the interpolymer (or fraction) is greater than 3, preferably from 3 to 5.

#### Crystallization Onset Temperature Measurement

The crystallization onset temperatures of the polyethylene compositions described herein are measured using differential scanning calorimetry (DSC). Each sample to be tested is made into a compression molded plaque according to ASTM D 1928. The plaques are then thinly sliced at room temperature using a Reichert Microtome or a razor blade to obtain samples having a thickness of about 15 micrometers. About 5 milligrams of each sample to be tested is placed in the DSC pan and heated to about 180°C, held at that temperature for 3 minutes to destroy prior heat history, cooled to -50°C at a rate of 10°C/minute and held at that temperature for 2 minutes. The crystallization onset temperature and the peak temperature are recorded by the DSC as the temperature at which crystallization begins and the temperature at which the sample is as fully crystallized as possible, respectively, during the cooling period from 180°C to -50°C.

Other useful physical property determinations made on the novel interpolymer compositions described herein include:

Melt flow ratio (MFR): measured by determining "I<sub>10</sub>" (according to ASTM D-1238, Condition 190°C/10 kg (formerly known as "Condition (N)")) and dividing the obtained I<sub>10</sub> by the I<sub>2</sub>. The ratio of these two melt index terms is the melt flow ratio and is designated as I<sub>10</sub>/I<sub>2</sub>. For the homogeneous portion of the interpolymer composition, the I<sub>10</sub>/I<sub>2</sub> ratio is generally greater than or equal to 5.63 and preferably from 5.8 to 8.5. For the heterogeneous portion of the interpolymer composition, the I<sub>10</sub>/I<sub>2</sub> ratio is typically from 6.8 to 9.5. The I<sub>10</sub>/I<sub>2</sub>

ratio for the whole interpolymer compositions is typically from 6.8 to 10.5.

2% Secant Modulus: using a method similar to ASTM D 882, except that 4 specimens are used, a 4 (18 cm) inch gauge length is used  
5 and the conditioning period is 24 hours;

Clarity: measured by specular transmittance according to ASTM D 1746, except that the samples are conditioned for 24 hours;

Haze: measured according to ASTM D 1003.

Young's modulus, yield strength and elongation, break strength  
10 and elongation, and toughness: using a method similar to ASTM D 882, except that 4 specimens are used and are pulled at 20 inches per minute (50 cm/min) using a 2 inch (5 cm) gauge length;

Spencer Impact: using a method similar to ASTM D 3420, procedure "B", except that the maximum capacity is 1600 grams, the values  
15 are normalized for sample thickness and the conditioning period has been shortened from 40 hours to 24 hours; and

Tensile Tear: using a method similar to ASTM D 1938, except that 4 specimens are used.

20 Useful articles which can be made from such interpolymer compositions include films (e.g., cast film, blown film or extrusion coated types of film), fibers (e.g., staple fibers, melt blown fibers or spunbonded fibers (using, e.g., systems as disclosed in USP 4,340,563, USP 4,663,220, USP 4,668,566, or USP 4,322,027), and gel spun fibers (e.g.,  
25 the system disclosed in USP 4,413,110)), both woven and nonwoven fabrics (e.g., spunlaced fabrics disclosed in USP 3,485,706) or structures made from such fibers (including, e.g., blends of these fibers with other fibers, e.g., PET or cotton)), and molded articles (e.g., blow molded articles, injection molded articles and rotomolded articles).

30 Films particularly benefit from such interpolymer compositions. Films and film structures having the novel properties described herein can be made using conventional hot blown film fabrication techniques or other biaxial orientation process such as tenter frames or double bubble processes. Conventional hot blown film processes are  
35 described, for example, in The Encyclopedia of Chemical Technology, Kirk-Othmer, Third Edition, John Wiley & Sons, New York, 1981, Vol. 16, pp.

416-417 and Vol. 18, pp. 191-192. Biaxial orientation film manufacturing process such as described in a "double bubble" process as in U.S. Patent 3,456,044 (Pahlke), and the processes described in U.S. Patent 4,865,902 (Golike et al.), U.S. Patent 4,352,849 (Mueller), U.S. Patent 4,820,557 (Warren), U.S. Patent 4,927,708 (Herran et al.), U.S. Patent 4,963,419 (Lustig et al.), and U.S. Patent 4,952,451 (Mueller) can also be used to make novel film structures from the novel interpolymer compositions. Novel property combinations of such films include unexpectedly high machine and cross direction secant modulus, both first and second machine and cross direction yield, dart impact, cross direction tensile, clarity, 20° gloss, 45° gloss, low haze, low blocking force and low coefficient of friction (COF).

In addition, these interpolymer compositions have better resistance to melt fracture. An apparent shear stress vs. apparent shear rate plot is used to identify the melt fracture phenomena. According to Ramamurthy in Journal of Rheology, 30(2), 337-357, 1986, above a certain critical flow rate, the observed extrudate irregularities may be broadly classified into two main types: surface melt fracture and gross melt fracture.

Surface melt fracture occurs under apparently steady flow conditions and ranges in detail from loss of specular gloss to the more severe form of "sharkskin". In this disclosure, the onset of surface melt fracture is characterized at the beginning of losing extrudate gloss at which the surface roughness of extrudate can only be detected by 40X magnification. The critical shear rate at onset of surface melt fracture for the substantially linear olefin polymers is at least 50 percent greater than the critical shear rate at the onset of surface melt fracture of a linear olefin polymer having about the same I2 and Mw/Mn.

Gross melt fracture occurs at unsteady flow conditions and ranges in detail from regular (alternating rough and smooth, helical, etc.) to random distortions. For commercial acceptability, (e.g., in blown film products), surface defects should be minimal, if not absent. The critical shear rate at onset of surface melt fracture (OSMF) and onset of gross melt fracture (OGMF) will be used herein based on the changes of surface roughness and configurations of the extrudates extruded by a GER.



Example 1Homogeneous Catalyst Preparation

A known weight of the constrained-geometry organometallic complex  $\{[(CH_3)_4C_5]-(CH_3)_2Si-N-(t-C_4H_9)]Ti(CH_3)_2$  was dissolved in Isopar E to give a clear solution with a concentration of Ti of 0.005M. A similar solution of the activator complex, tris(perfluorophenyl)borane (0.010M) was also prepared. A catalyst composition of a few mL total volume was prepared by adding 2.0 mL of Isopar E solution of Ti reagent, 2.0 mL of the borane (for B:Ti = 2:1) and 2 mL Isopar E to a 4 oz (100 ml) glass bottle. The solution was mixed for a few minutes and transferred by syringe to a catalyst injection cylinder on the polymerization reactor.

Heterogeneous Catalyst Preparation

A heterogeneous Ziegler-type catalyst was prepared substantially according to USP 4,612,300 (Ex. P.), by sequentially adding to a volume of Isopar E, a slurry of anhydrous magnesium chloride in Isopar E, a solution of  $EtAlCl_2$  in hexane, and a solution of  $Ti(O-iPr)_4$  in Isopar E, to yield a composition containing a magnesium concentration of 0.17M and a ratio of Mg/Al/Ti of 40/12/3. An aliquot of this composition containing 0.064 mmol of Ti which was treated with a dilute solution of  $Et_3Al$  to give an active catalyst with a final Al/Ti ratio of 8/1. This slurry was then transferred to a syringe until it was required for injection into the polymerization reactor.

Polymerization

The polymerization described in this example demonstrates a process for the use of two catalysts, employed sequentially, in two polymerization reactors. A stirred, one-gallon (3.79L) autoclave reactor is charged with 2.1 L of Isopar™ E (made by Exxon Chemical) and 388 mL of 1-octene comonomer and the contents are heated to 150°C. The reactor is next charged with ethylene sufficient to bring the total pressure to 450 psig (3.2 MPa). A solution containing 0.010 mmol of the active organometallic catalyst described in the catalyst preparation section is

injected into the reactor using a high pressure nitrogen sweep. The reactor temperature and pressure are maintained constant at the desired final pressure and temperature by continually feeding ethylene during the polymerization run and cooling the reactor as necessary. After a 10  
5 minute reaction time, the ethylene is shut off and the reactor is depressured to 100 psig (0.8 MPa). Hydrogen is admitted to the reactor and the contents heated. A slurry of the heterogeneous catalyst containing 0.0064 mmol Ti prepared as described in the catalyst preparation section is injected into the reactor using a high pressure  
10 nitrogen sweep. The reactor is then continually fed ethylene at 450 psig (3.2 MPa) and the reaction temperature quickly rose to 185°C where the polymerization is sustained for an additional 10 minutes. At this time the reactor is depressured and the hot polymer-containing solution transferred into a nitrogen-purged resin kettle containing 0.2 g Irganox  
15 1010 antioxidant as a stabilizer. After removal of all the solvent in vacuo, the sample is then weighed (yield 270 g) to determine catalyst efficiencies (344300 g PE/ g Ti).

#### Examples 2 and 3

20 Examples 2 and 3 are carried out as in Example 1 except using the catalyst amounts and reactor temperatures described in Table 1. The overall catalyst efficiencies are also shown in the Table.

The polymer products of Examples 1-3 are tested for various  
25 structural, physical and mechanical properties and the results are given in Tables 2, 2A and 2B. Comparative Example A is Attane® 4001 polyethylene and comparative example B is Attane® 4003. Both comparative examples are made by The Dow Chemical Company and are commercial ethylene-octene copolymers produced under solution process conditions using a  
30 typical commercial Ziegler-type catalyst. The data show the polymers of the invention have more narrow molecular weight distributions ( $M_w/M_n$ ), higher melting points, better crystallization properties (i.e., higher crystallization onset temperatures) and, surprisingly, higher modulus than the commercial comparative examples A and B. The polymers of the  
35 invention surprisingly also show better optical properties (i.e., higher clarity and lower haze) than the comparative polymers, even though the

polymers have about the same density. In addition, the polymers of the invention show better strength, toughness, tear and impact properties.

Table 1

Process Conditions for Reactor #1 for Examples 1-3

Ex.	Monomer Volume (ml)	Reactor #1 Temp. (°C)	H <sub>2</sub> (Reactor #1) (mmol)	Catalyst #1 (micromoles)
1	300	154	0	10
2	300	141	0	5
3	300	134	0	4

5

Table 1A

Process Conditions for Reactor #2 for Examples 1-3

Ex.	Monomer Volume (ml)	Reactor #2 Temp. (°C)	H <sub>2</sub> (Reactor #2) (mmol)	Catalyst #2 (micromoles)	Overall Titanium Efficiency (g PE/g Ti)
1	300	185	100	6.4	344300
2	300	191	100	9	410100
3	300	193	100	9	425600

Table 2

Examples 1-3 and Comparative Examples A and B

Ex.	Density (g/cm <sup>3</sup> )	Melt Index (I <sub>2</sub> ) (g/10 min)	MFR (I <sub>10</sub> /I <sub>2</sub> )	M <sub>w</sub>	M <sub>n</sub>	MWD (M <sub>w</sub> /M <sub>n</sub> )
A	0.9136	1.06	8.33	122500	32500	3.77
B	0.9067	0.79	8.81	135300	31900	4.25
1	0.9112	1.07	7.4	115400	40000	2.89
2	0.9071	1.23	7.32	117600	40300	2.92
3	0.9062	1.08	7.46	124500	40100	3.1

10

Table 2A

Ex.	Melting Temp. (°C)	Crystl. Onset Temp. (°C)	2% Secant Modulus	Young's Modulus (psi)	Clarity (specular trans.)	Haze (%)
A	121	105	20389	20425	0.85	67
B	121	105	13535	13541	1.32	56
1	124	111	25634	25696	2.7	65
2	123	111	28144	28333	5.5	62
3	123	111	28650	28736	3.7	61

Table 2B

Ex.	Yield Strength (psi)	Yield Elongation (%)	Break Strength (psi)	Break Elongation (%)	Toughness (ft.-lb.)	Spencer Impact (psi)	Tensile Strength (g/mil)
A	1370	22	3133	693	1003	847	265
B	1108	24	2450	667	793	688	215
1	1541	16	4134	642	1155	897	311
2	1717	16	5070	658	1327	908	290
3	1756	15	4679	637	1234	903	311

#### 5 Example 4

##### Homogeneous Catalyst Preparation

A known weight of the constrained-geometry organometallic complex  $\{[(CH_3)_4C_5]-(CH_3)_2Si-N-(t-C_4H_9)]Ti(CH_3)_2$  is dissolved in Isopar E to give a clear solution with a concentration of Ti of 0.001M. A similar  
 10 solution of the activator complex, tris(perfluorophenyl)borane (0.002M) is also prepared. A catalyst composition of a few mL total volume is prepared by adding 1.5 mL of Isopar E solution of Ti reagent, 1.5 mL of the borane (for B:Ti = 2:1) and 2 mL of a heptane solution of methylaluminoxane (obtained commercially from Texas Alkyls as MMAO Type  
 15 3A) containing 0.015 mmol Al to a 4 oz (100 ml) glass bottle. The solution is mixed for a few minutes and transferred by syringe to a catalyst injection cylinder on the polymerization reactor.

##### Heterogeneous Catalyst Preparation

20 A heterogeneous Ziegler-type catalyst is prepared similarly to that in Ex. 1 to give an active catalyst containing 0.009 mmol Ti and a final Al/Ti ratio of 8/1. This slurry is then transferred to a syringe in preparation for addition to the catalyst injection cylinder on the polymerization reactor.

Polymerization

A stirred, one-gallon (3.79L) autoclave reactor is charged with 2.1 L of Isopar™ E (made by Exxon Chemical) and 168 mL of 1-octene comonomer and the contents are heated to 120°C. The reactor is next charged with hydrogen and then with ethylene sufficient to bring the total pressure to 450 psig (3.2MPa). A solution containing 0.0015 mmol of the active organometallic catalyst described in the catalyst preparation section is injected into the reactor using a high pressure nitrogen sweep. The reactor temperature and pressure are maintained at the initial run conditions. After a 10 minute reaction time, the ethylene is shut off and the reactor is depressured to 100 psig (0.8MPa). At this time, an additional 168 mL of 1-octene is added to the reactor along with additional hydrogen and the contents heated. A slurry of the heterogeneous catalyst containing 0.009 mmol Ti prepared as described in the catalyst preparation section is injected into the reactor using a high pressure nitrogen sweep. The reactor is then continually fed ethylene at 450 psig (3.2MPa) and the reaction temperature quickly rises to 189°C where the polymerization is sustained for an additional 10 minutes. At this time the reactor is depressured and the hot polymer-containing solution transferred into a nitrogen-purged resin kettle containing 0.2 g Irganox™ 1010 (a hindered phenolic antioxidant made by Ciba Geigy Corp.) as a stabilizer. After removal of all the solvent in vacuo, the sample is then weighed (yield 202 g) to determine catalyst efficiencies (401630 g PE/ g Ti).

Examples 5-7

Examples 5-7 are carried out as in Example 4 except using the catalysts described in Example 1 and the catalyst amounts and reactor conditions described in Tables 3 and 3A. The overall catalyst efficiencies are also shown in Tables 3 and 3A.

These examples show that the reaction conditions can be readily controlled to vary the composition and molecular weight distribution of the polymer through a simple change in catalyst amounts and monomer concentrations. Table 4 shows that the interpolymers produced

in these examples have a broader molecular weight distribution than those of the earlier examples demonstrating a unique feature of the process control. The physical and mechanical properties still show surprising enhancements over typical commercial copolymers of comparable molecular weight and composition, particularly in strength, impact and tear properties. Comparing examples 4 and 5 with comparative example A (as well as by comparing examples 6 and 7 with comparative example B) shows that the crystallization properties of the polymers of the invention are largely unaffected by broadening the  $M_w/M_n$ .

10

Table 3

Process Conditions for Reactor #1 for Examples 4-7

Ex.	Monomer Volume (ml)	Reactor #1 Temp. (°C)	Reactor #1 H <sub>2</sub>	Catalyst #1 (micromoles)	Overall Titanium Efficiency (g PE/g Ti)
4	150+150	123	10	1.5	401630
5	150+150	139	50	5	422670
6	300+150	122	0	4	337241
7	300+150	133	100	6	434933

Table 3A

Process Conditions for Reactor #2 for Examples 4-7

Ex.	Monomer Volume (ml)	Reactor #2 Temp. (°C)	Reactor #2 H <sub>2</sub> (mmol)	Catalyst #2 (micromoles)	Overall Titanium Efficiency (g PE/g Ti)
4	150+150	189	300	9	401630
5	150+150	194	50	7.2	422670
6	300+150	189	400	9	337241
7	300+150	188	50	7.2	434933

Table 4

Interpolymer Properties

Ex.	Density (g/cm <sup>3</sup> )	Melt Index (I <sub>2</sub> ) (g/10 min)	MFR (I <sub>10</sub> /I <sub>2</sub> )	M <sub>w</sub>	M <sub>n</sub>	MWD (M <sub>w</sub> /M <sub>n</sub> )
A	0.9136	1.06	8.33	122500	32500	3.77
4	0.913	1.12	7.45	117900	29400	4.003
5	0.9136	1.17	8.07	135000	42100	3.209
B	0.9067	0.79	8.81	135300	31900	4.25
6	0.9108	3.3	7.4	89700	28700	3.122
7	0.9081	1.53	10.17	125700	31000	4.057

Table 4A

Ex.	Melting peak (°C)	Cryst. Onset Temp. (°C)	Young's Modulus (psi)	2% Secant Modulus	Clarity (specular trans.)	Haze (%)
A	121	105	20425	20389	0.85	67
4	123	110	20333	20292	4.7	72
5	123	110	22648	22609	2.32	72
B	121	105	13541	13535	1.32	56
6	124	112	20100	20074	1.15	72
7	123	112	19836	19800	1.85	67

Table 4B

Ex.	Yield strength (psi)	Yield elongation (%)	Break strength (psi)	Break elongation (%)	Toughness (ft-lbs)	Spencer Impact (psi)	Tensile Tear (g/mil)
A	1370	22	3133	693	1003	847	265
4	1468	19	3412	671	1012	977	271
5	1659	16	3608	738	1224	994	313
B	1108	24	2450	667	793	688	215
6	1354	16	2737	670	885	1022	255
7	1326	21	2353	729	914	821	238



Example 8Homogeneous Catalyst Preparation

A known weight of the constrained-geometry organometallic complex  $\{[(CH_3)_4C_5]-(CH_3)_2Si-N-(t-C_4H_9)]Ti(CH_3)_2$  is dissolved in Isopar E to give a clear solution with a concentration of Ti of 0.001M. A similar solution of the activator complex, tris(perfluorophenyl)borane (0.002M) is also prepared. A catalyst composition of a few mL total volume is prepared by adding 1.5 mL of Isopar E solution of Ti reagent, 1.5 mL of the borane (for B:Ti = 2:1) and 2 mL of a heptane solution of methylaluminoxane (obtained commercially from Texas Alkyls as MMAO) containing 0.015 mmol Al to a 4 oz (100 ml) glass bottle. The solution is mixed for a few minutes and transferred by syringe to a catalyst injection cylinder on the polymerization reactor.

Heterogeneous Catalyst Preparation

A heterogeneous Ziegler-type catalyst is prepared similarly to that in Ex. 1 to give an active catalyst containing 0.009 mmol Ti and a final Al/Ti ratio of 8/1. This slurry is then transferred to a syringe in preparation for addition to the catalyst injection cylinder on the polymerization reactor.

Polymerization

The polymerization described in this example demonstrates a process for the use of two catalysts, employed sequentially, in two polymerization reactors. A stirred, one-gallon (3.79L) autoclave reactor is charged with 2.1 L of Isopar™ E (made by Exxon Chemical) and 168 mL of 1-octene comonomer and the contents are heated to 120°C. The reactor is next charged with hydrogen and then with ethylene sufficient to bring the total pressure to 450 psig (3.2 MPa). A solution containing 0.0015 mmol of the active organometallic catalyst described in the catalyst preparation section is injected into the reactor using a high pressure nitrogen sweep. The reactor temperature and pressure are maintained at the initial run conditions. After a 10 minute reaction time, the ethylene is shut off and the reactor is depressured to 100 psig (0.8 MPa). At this time, an additional 168 mL of 1-octene is added to the reactor along with additional hydrogen and the contents heated. A slurry of the

heterogeneous catalyst containing 0.009 mmol Ti prepared as described in the catalyst preparation section is injected into the reactor using a high pressure nitrogen sweep. The reactor is then continually fed ethylene at 450 psig (3.2MPa) and the reaction temperature quickly rises to 189°C where the polymerization is sustained for an additional 10 minutes. At this time the reactor is depressured and the hot polymer-containing solution transferred into a nitrogen-purged resin kettle containing 0.2 g Irganox™ 1010 (a hindered phenolic antioxidant made by Ciba Geigy Corp.) as a stabilizer. After removal of all the solvent in vacuo, the sample is then weighed (yield 202 g) to determine catalyst efficiencies (401630 g PE/ g Ti).

#### Examples 9-14

Examples 9-14 are carried out as in Example 8 except using the catalysts described in Example 1 and the catalyst amounts and reactor conditions described in Tables 5 and 5A. The overall catalyst efficiencies are also shown in the Tables.

These examples show the ability to readily control the reaction conditions to vary the composition and molecular weight distribution of the polymer through a simple change in catalyst amounts and monomer concentrations. The polymers produced in these Examples show a broader molecular weight distribution than those of the earlier examples showing a unique feature of the process control. The physical and mechanical properties still show surprising enhancements over typical commercial copolymers of comparable molecular weight and composition, particularly in strength, impact and tear properties.

Comparative Example C is Dowlex® 2045, a commercial ethylene/1-octene copolymer made by The Dow Chemical Company. Comparative Example D is Dowlex® 2047, a commercial LLDPE ethylene/1-octene copolymer made by The Dow Chemical Company.

The data in Table 6 show that the molecular weight distribution ( $M_w/M_n$ ) can surprisingly remain relatively low, demonstrating a unique feature of the process control of the invention.

Table 5  
Process Conditions for Reactor #1 for Examples 8-14

Ex.	Monomer Volume (ml)	Reactor #1 Temp (°C)	Reactor #1 H <sub>2</sub> (mmol)	Catalyst #1 (micromoles)	Overall Titanium Efficiency (g PE/g Ti)
8	155	158	25	12.5	286100
9	155	146	20	7.5	312400
10	155	156	0	7.5	326600
11	205	155	0	10	311900
12	230	149	0	7.5	312400
13	155	152	0	7.5	305300
14	150+150	145	0	7.5	298200

Table 5A  
Process Conditions for Reactor #2 for Examples 8-14

Ex.	Monomer Volume (ml)	Reactor #2 Temp (°C)	Reactor #2 H <sub>2</sub> (mmol)	Catalyst #2 (micromoles)	Overall Titanium Efficiency (g PE/g Ti)
8	155	190	150	7.2	286100
9	155	170	150	7.2	312400
10	155	188	200	7.2	326600
11	205	194	150	7.2	311900
12	230	194	150	7.2	312400
13	155	196	400	7.2	305300
14	150+150	195	150	7.2	298200

Table 6

Ex.	Density (g/cm <sup>3</sup> )	Melt Index (I <sub>2</sub> ) (g/10 min)	MFR (I <sub>10</sub> /I <sub>2</sub> )	M <sub>w</sub>	M <sub>n</sub>	MWD (M <sub>w</sub> /M <sub>n</sub> )
C	0.9202	1	ND	110000	27300	4.03
8	0.9257	3.1	6.72	80400	32000	2.5
9	0.9225	1.43	6.89	99400	36800	2.7
10	0.9234	1.57	7.04	100400	35200	2.85
D	0.9171	2.3	ND	85500	22000	3.89
11	0.9158	1.39	7.15	100000	35100	2.85
12	0.916	0.91	7.16	113200	37700	3
13	0.915	0.84	7.94	106900	33300	3.21
14	0.9186	1.09	7.1	106200	36400	2.9

ND = Not Determined

5

Table 6A

Ex.	Melt. Peak (°C)	Crystal. Onset Temp. (°C)	2% Secant Modulus	Young's Modulus (psi)	Clarity (Specular Trans.)	Haze (%)
C	ND	107	29169	29253	3.55	55
8	123	111	48123	48209	0.15	75
9	124	111	47815	47906	0.72	78
10	124	114	34077	34742	0.15	72
D	ND	ND	26094	26094	1.22	49
11	124	113	26245	26304	0.22	69
12	123	111	35492	35599	0.47	67
13	122	110	26466	26534	1.37	63
14	124	111	34989	35032	0.77	66

ND = Not Determined

Table 6B

Ex.	Yield Strength (psi)	Yield elongation (%)	Break strength (psi)	Break elongation (%)	Toughness (ft-lb)	Spencer Impact (psi)	Tensile Tear (g/mil)
C	1830	13	4395	689	1292	735	316
8	2628	12	3893	620	1335	992	450
9	2403	13	4375	613	1343	753	367
10	2240	13	3619	600	1179	1043	326
D	1600	15	4061	771	1351	716	285
11	1905	15	5079	700	1480	820	334
12	2043	15	5385	610	1404	976	336
13	1818	21	4504	612	1203	977	247
14	1933	16	4755	653	1332	741	283

In step (B) of the Second Process, the ethylene and  $\alpha$ -olefin materials may be present as unreacted materials in the reaction product from step (A) or they can each be added to the polymerization reaction mixture in step (B) as needed to make the desired interpolpolymer. In addition, hydrogen or other telogen can be added to the polymerization mixture of step (B) to control molecular weight.

#### 10 Example 15

Example 15 is an *in-situ* blend made according to a continuous polymerization process. In particular, ethylene is fed into a first reactor at a rate of 52 lb/hr (24 kg/hr). Prior to introduction into the first reactor, the ethylene is combined with a diluent mixture comprising 15 ISOPAR<sup>TM</sup> E hydrocarbon (available from Exxon) and 1-octene. With respect to the first reactor, the 1-octene:ethylene ratio is 9.6:1 (mole percent) and the diluent:ethylene ratio is 9.9:1 (weight). A homogenous constrained geometry catalyst and cocatalyst such as are described in Example 8 above and introduced into the first reactor. The catalyst and 20 cocatalyst concentrations in the first reactor are 0.0030 and 0.0113 molar, respectively. The catalyst and cocatalyst flow rates into the first reactor are 0.537 lbs/hr (0.224 kg/hr) and 0.511 lbs/hr (0.232 kg/hr), respectively. The polymerization is conducted at a reaction temperature of 120°C. The polymer of the first reactor is an ethylene/1-octene copolymer and is estimated to have a density of 0.906 g/cm<sup>3</sup>, a melt 25 flow ratio ( $I_{10}/I_2$ ) of about 8-10 and a molecular weight distribution ( $M_w/M_n$ ) of 2.2.

The reaction product of the first reactor is transferred to a second reactor. The ethylene concentration in the exit stream from the first reactor is less than four percent, indicating the presence of long chain branching as described in U.S. Patent No. 5, 272,236.

5           Ethylene is further fed into a second reactor at a rate of 58 lbs/hr (26 kg/hr). Prior to introduction into the second reactor, the ethylene and a stream of hydrogen are combined with a diluent mixture comprising ISOPAR™ E hydrocarbon (available from Exxon) and 1-octene. With respect to the second reactor, the 1-octene:ethylene ratio is 2.9:1  
10 (mole percent), the diluent:ethylene ratio is 2.8 (weight), and the hydrogen:ethylene ratio is 0.106 (mole percent). A heterogeneous Ziegler catalyst and cocatalyst such as are described in Example 1 above are introduced into the second reactor. The catalyst and cocatalyst concentrations in the second reactor are 0.0023 and 0.0221 molar,  
15 respectively. The catalyst and cocatalyst flow rates into the second reactor are 1.4 lbs/hr (0.64 kg/hr) and 0.858 lbs/hr (0.39 kg/hr), respectively. The polymerization is conducted at a reaction temperature of 190°C. The polymer of the second reactor is an ethylene/1-octene copolymer and estimated to have a density of 0.944 g/cm<sup>3</sup> and a melt index  
20 (I<sub>2</sub>) of 1.5 g/10 minutes.

The total composition comprises 43 percent by weight of the polymer of the first reactor and 57 percent by weight of the polymer of the second reactor. The total composition has a melt index (I<sub>2</sub>) of 0.53 g/10 minutes, a density of 0.9246 g/cm<sup>3</sup>, a melt flow ratio (I<sub>10</sub>/I<sub>2</sub>) of  
25 7.83, and a molecular weight distribution (M<sub>w</sub>/M<sub>n</sub>) of 2.8.

## CLAIMS:

1. A process for preparing an ethylene/a-olefin interpolymer composition, characterized by:

(A) reacting by contacting ethylene and at least one other a-olefin under solution polymerization conditions in the presence of a homogeneous catalyst composition containing either no aluminum cocatalyst or only a small amount of aluminum cocatalyst in at least one reactor to produce a solution of a first interpolymer which has a narrow composition distribution and a narrow molecular weight distribution,

(B) reacting by contacting ethylene and at least one other a-olefin under solution polymerization conditions and at a higher polymerization reaction temperature than used in step (A) in the presence of a heterogeneous Ziegler catalyst in at least one other reactor to produce a solution of a second interpolymer which has a broad composition distribution and a broad molecular weight distribution, wherein the Ziegler catalyst comprises

(i) a solid support component derived from a magnesium halide or silica, and

(ii) a transition metal component represented by the formulas:  $\text{TrX}'_4\text{-q(OR}^1\text{)}_q$ ,  $\text{TrX}'_4\text{-qR}^2_q$ ,  $\text{VOX}'_3$  and  $\text{VO (OR}^1\text{)}_3$ , wherein:

Tr is a Group IVB, VB, or VIB metal,

q is 0 or a number equal to or less than 4,

X' is a halogen, and

R<sup>1</sup> is an alkyl group, aryl group or cycloalkyl group having from 1 to 20 carbon atoms, and

R<sup>2</sup> is an alkyl group, aryl group, aralkyl group, or substituted aralkyl group, and

(C) combining the solution of the first interpolymer with the solution of the second interpolymer to form a high temperature polymer solution comprising the ethylene/a-olefin interpolymer composition, and

(D) removing the solvent from the polymer solution of step (C) and recovering the ethylene/a-olefin interpolymer composition.

2. The ethylene/a-olefin interpolymer composition produced by the process of Claim 1.


3. The process of Claim 1 wherein the  $\alpha$ -olefin in each of steps (A) and (B) is 1-octene.

4. The ethylene/1-octene interpolymer composition produced by the process of Claim 3.

5. The process of Claim 1 wherein the homogeneous catalyst composition comprises a metal coordination complex comprising a metal of group 4 of the Periodic Table of the Elements and a delocalized  $\pi$ -bonded moiety substituted with a constrain-inducing moiety, said complex having a constrained geometry about the metal atom such that the angle at the metal between the centroid of the delocalized, substituted  $\pi$ -bonded moiety and the center of at least one remaining substituent is less than such angle in a similar complex containing a similar  $\pi$ -bonded moiety lacking in such constrain-inducing substituent, and provided further that for such complexes comprising more than one delocalized, substituted  $\pi$ -bonded moiety, only one thereof for each metal atom of the complex is a cyclic, delocalized, substituted  $\pi$ -bonded moiety.

6. The process of Claim 5 wherein the homogeneous catalyst composition further comprises an activating cocatalyst.

7. The process of Claim 5 wherein the metal coordination complex corresponds to the formula:





wherein:

M is a metal of group 4 of the Periodic Table of the Elements;

5

Cp\* is a cyclopentadienyl or substituted cyclopentadienyl group bound in an  $h^5$  bonding mode to M;


10 Z is a moiety comprising boron, or a member of group 14 of the Periodic Table of the Elements, and optionally sulfur or oxygen, said moiety having up to 20 non-hydrogen atoms, and optionally Cp\* and Z together form a fused ring system;

15 X independently each occurrence is an anionic ligand group having up to 30 non-hydrogen atoms;

n is 1 or 2; and

20 Y is an anionic or nonanionic ligand group bonded to Z and M comprising nitrogen, phosphorus, oxygen or sulfur and having up to 20 non-hydrogen atoms, optionally Y and Z together form a fused ring system.

8. The process of Claim 5 wherein the metal coordination complex corresponds to the formula:



25

wherein:

R' each occurrence is independently selected from the group consisting of hydrogen, alkyl, aryl, and silyl, and combinations thereof having up to 20 non-hydrogen atoms;

5 X each occurrence independently is selected from the group consisting of hydride, halo, alkyl, aryl, silyl, aryloxy, alkoxy, amide, siloxy and combinations thereof having up to 20 non-hydrogen atoms;


10 Y is -O-, -S-, -NR\*-, -PR\*-, or a neutral two electron donor ligand selected from the group consisting of OR\*, SR\*, NR\*<sub>2</sub> or PR\*<sub>2</sub>;

M is as previously defined; and

15 Z is SiR\*<sub>2</sub>, CR\*<sub>2</sub>, SiR\*<sub>2</sub>SiR\*<sub>2</sub>, CR\*<sub>2</sub>CR\*<sub>2</sub>, CR\*=CR\*, CR\*<sub>2</sub>SiR\*<sub>2</sub>, BR\*; wherein

R\* each occurrence is independently selected from the group consisting of hydrogen, alkyl, aryl, silyl, halogenated alkyl, halogenated aryl groups having up to 20 non-hydrogen atoms, and mixtures thereof, or  
20 two or more R\* groups from Y, Z, or both Y and Z form a fused ring system; and n is 1 or 2.

9. The process of Claim 5 wherein the metal coordination complex is an amidosilane- or amidoalkanedyl- compound corresponding to  
25 the formula:



wherein:

M is titanium, zirconium or hafnium, bound in an  $h^5$  bonding mode to the cyclopentadienyl group;

5 R' each occurrence is independently selected from the group consisting of hydrogen, alkyl and aryl and combinations thereof having up to 7 carbon atoms, or silyl;


E is silicon or carbon;

10 X independently each occurrence is hydride, halo, alkyl, aryl, aryloxy or alkoxy of up to 10 carbons, or silyl;

m is 1 or 2; and

15 n is 1 or 2.

10. The process of Claim 5 wherein the metal coordination complex is an ionic catalyst having a limiting charge separated structure  
20 corresponding to the formula:



wherein:

25 M is a metal of group 4 of the Periodic Table of the Elements;

Cp\* is a cyclopentadienyl or substituted cyclopentadienyl group bound in an  $h^5$  bonding mode to M;

Z is a moiety comprising boron, or a member of group 14 of the Periodic Table of the Elements, and optionally sulfur or oxygen, said moiety having up to 20 non-hydrogen atoms, and optionally Cp\* and Z together form a fused ring system;

5

X independently each occurrence is an anionic ligand group having up to 30 non-hydrogen atoms;

n is 1 or 2; and

10

XA\* - is  $\text{X}(\text{B}(\text{C}_6\text{F}_5)_3)$ .

11. The process of Claim 1 wherein the homogeneous catalyst composition has a reactivity ratio less than half that of the heterogeneous catalyst.

15

12. A process for preparing an ethylene/a-olefin interpolymer composition, characterized by:

(A) polymerizing ethylene and at least one other a-olefin in a solution process under suitable solution polymerization temperatures and pressures in at least one reactor containing a homogeneous catalyst composition containing either no aluminum cocatalyst or only a small amount of aluminum cocatalyst to produce a first interpolymer solution comprising a first interpolymer having a narrow composition distribution and a narrow molecular weight distribution, and

25

(B) sequentially passing the interpolymer solution of (A) into at least one other reactor containing a heterogeneous Ziegler catalyst, ethylene and at least one other a-olefin under solution polymerization conditions and at a polymerization temperature higher than that used in (A), to form a high temperature polymer solution comprising the ethylene/a-olefin interpolymer composition, wherein the Ziegler catalyst comprises

30

(i) a solid support component derived from a magnesium halide or silica, and

35

(ii) a transition metal component represented by the formulas:  $\text{TrX}'_4\text{-q}(\text{OR}^1)_q$ ,  $\text{TrX}'_4\text{-qR}^2_q$ ,  $\text{VOX}'_3$  and  $\text{VO}(\text{OR}^1)_3$ , wherein:

Tr is a Group IVB, VB, or VIB metal,

q is 0 or a number equal to or less than 4,

X' is a halogen, and

R<sup>1</sup> is an alkyl group, aryl group or cycloalkyl group having  
5 from 1 to 20 carbon atoms, and

R<sup>2</sup> is an alkyl group, aryl group, aralkyl group, or  
substituted aralkyl group, and

(C) removing the solvent from the polymer solution of step (B) and  
recovering the ethylene/a-olefin interpolymer composition.

10

13. The ethylene/a-olefin interpolymer composition produced by  
the process of Claim 12.

15


14. The process of Claim 12 wherein the a-olefin is 1-octene.

15. The ethylene/1-octene interpolymer composition produced by  
the process of Claim 14.

16. The process of Claim 12 wherein the homogeneous catalyst  
20 composition comprises a metal coordination complex comprising a metal of  
group 4 of the Periodic Table of the Elements and a delocalized  $\pi$ -bonded  
moiety substituted with a constrain-inducing moiety, said complex having a  
constrained geometry about the metal atom such that the angle at the metal  
between the centroid of the delocalized, substituted  $\pi$ -bonded moiety and  
25 the center of at least one remaining substituent is less than such angle  
in a similar complex containing a similar  $\pi$ -bonded moiety lacking in such  
constrain-inducing substituent, and provided further that for such  
complexes comprising more than one delocalized, substituted  $\pi$ -bonded  
moiety, only one thereof for each metal atom of the complex is a cyclic,  
30 delocalized, substituted  $\pi$ -bonded moiety.

17. The process of Claim 12 wherein the homogeneous catalyst composition further comprises an activating cocatalyst.

18. The process of Claim 16 wherein the metal coordination  
5 complex corresponds to the formula:



wherein:

10

M is a metal of group 4 of the Periodic Table of the Elements;

Cp\* is a cyclopentadienyl or substituted cyclopentadienyl group bound in an  $h^5$  bonding mode to M;

15

Z is a moiety comprising boron, or a member of group 14 of the Periodic Table of the Elements, and optionally sulfur or oxygen, said moiety having up to 20 non-hydrogen atoms, and optionally Cp\* and Z together form a fused ring system;

20


X independently each occurrence is an anionic ligand group having up to 30 non-hydrogen atoms;

n is 1 or 2; and

25

Y is an anionic or nonanionic ligand group bonded to Z and M comprising nitrogen, phosphorus, oxygen or sulfur and having up to 20 non-hydrogen atoms, optionally Y and Z together form a fused ring system.

- 5 19. The process of Claim 16 wherein the metal coordination complex corresponds to the formula:



- 10 wherein:

R' each occurrence is independently selected from the group consisting of hydrogen, alkyl, aryl, and silyl, and combinations thereof having up to 20 non-hydrogen atoms;

- 15 X each occurrence independently is selected from the group consisting of hydride, halo, alkyl, aryl, silyl, aryloxy, alkoxy, amide, siloxy and combinations thereof having up to 20 non-hydrogen atoms;

- 20 Y is -O-, -S-, -NR\*-, -PR\*-, or a neutral two electron donor ligand selected from the group consisting of OR\*, SR\*, NR\*<sub>2</sub> or PR\*<sub>2</sub>;


M is as previously defined; and

- 25 Z is SiR\*<sub>2</sub>, CR\*<sub>2</sub>, SiR\*<sub>2</sub>SiR\*<sub>2</sub>, CR\*<sub>2</sub>CR\*<sub>2</sub>, CR\*=CR\*, CR\*<sub>2</sub>SiR\*<sub>2</sub>, BR\*; wherein

R\* each occurrence is independently selected from the group consisting of hydrogen, alkyl, aryl, silyl, halogenated alkyl, halogenated aryl groups having up to 20 non-hydrogen atoms, and mixtures thereof, or

two or more R\* groups from Y, Z, or both Y and Z form a fused ring system;  
and n is 1 or 2.

20. The process of Claim 16 wherein the metal coordination  
5 complex is an amidosilane- or amidoalkanediy- compound corresponding to  
the formula:



wherein:

10 M is titanium, zirconium or hafnium, bound in an h<sup>5</sup> bonding  
mode to the cyclopentadienyl group;

R' each occurrence is independently selected from the group  
15 consisting of hydrogen, alkyl and aryl and combinations thereof having up  
to 7 carbon atoms, or silyl;

E is silicon or carbon;


20 X independently each occurrence is hydride, halo, alkyl, aryl,  
aryloxy or alkoxy of up to 10 carbons, or silyl;

m is 1 or 2; and

25 n is 1 or 2.



21. The process of Claim 16 wherein the metal coordination complex is an ionic catalyst having a limiting charge separated structure corresponding to the formula:



5 wherein:

M is a metal of group 4 of the Periodic Table of the Elements;

10 Cp\* is a cyclopentadienyl or substituted cyclopentadienyl group bound in an  $h^5$  bonding mode to M;

Z is a moiety comprising boron, or a member of group 14 of the Periodic Table of the Elements, and optionally sulfur or oxygen, said  
15 moiety having up to 20 non-hydrogen atoms, and optionally Cp\* and Z together form a fused ring system;

X independently each occurrence is an anionic ligand group having up to 30 non-hydrogen atoms;

20

n is 1 or 2; and

XA\*<sup>-</sup> is  $\text{X}(\text{B}(\text{C}_6\text{F}_5)_3)$ .

25

22. The process of Claim 12 wherein the homogeneous catalyst composition has a reactivity ratio less than half that of the heterogeneous catalyst.

**PCT**WORLD INTELLECTUAL PROPERTY ORGANIZATION  
International Bureau

## INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

<b>(51) International Patent Classification <sup>5</sup> :</b> C08F 297/08, C08L 23/08 C08F 210/16	<b>A3</b>	<b>(11) International Publication Number:</b> WO 94/17112 <b>(43) International Publication Date:</b> 4 August 1994 (04.08.94)
<b>(21) International Application Number:</b> PCT/US94/01052 <b>(22) International Filing Date:</b> 28 January 1994 (28.01.94) <b>(30) Priority Data:</b> 08/010,958 29 January 1993 (29.01.93) US <b>(71) Applicant:</b> THE DOW CHEMICAL COMPANY [US/US]; 2030 Dow Center, Abbott Road, Midland, MI 48640 (US). <b>(72) Inventors:</b> KOLTHAMMER, Brian, W., S.; 109 Rosewood Street, Lake Jackson, TX 77566 (US). CARDWELL, Robert, S.; 106 Any Way, Lake Jackson, TX 77566 (US). <b>(74) Agent:</b> WARRICK, Noreen, D.; The Dow Chemical Company, Patent Department, Building B-1211, Freeport, TX 77541 (US).		<b>(81) Designated States:</b> AU, BB, BG, BR, BY, CA, CN, CZ, FI, HU, JP, KR, KZ, LK, LU, LV, MG, MN, MW, NO, NZ, PL, PT, RO, RU, SD, SK, UA, UZ, European patent (AT, BE, CH, DE, DK, ES, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE).  <b>Published</b> <i>With international search report.</i> <i>Before the expiration of the time limit for amending the</i> <i>claims and to be republished in the event of the receipt of</i> <i>amendments.</i>  <b>(88) Date of publication of the international search report:</b> 15 September 1994 (15.09.94)
<b>(54) Title:</b> ETHYLENE INTERPOLYMERIZATIONS  <b>(57) Abstract</b>  Processes for polymerizing ethylene/a-olefin interpolymer compositions are disclosed. The interpolymer compositions have a controlled composition and a controlled molecular weight distribution. The processes utilize a highly-efficient homogeneous catalyst composition in at least one reactor to produce a first interpolymer having a narrow composition distribution and a narrow molecular weight distribution, and a highly-efficient heterogeneous Ziegler catalyst in at least one other reactor. The reactors can be operated sequentially or separately, depending upon the desired product. The novel compositions have good optical properties (e.g., clarity and haze) and good physical properties (e.g., modulus, yield strength, toughness and tear). Useful products which can be formed from these compositions include film, molded articles and fiber.		

**FOR THE PURPOSES OF INFORMATION ONLY**

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AT	Austria	GB	United Kingdom	MR	Mauritania
AU	Australia	GE	Georgia	MW	Malawi
BB	Barbados	GN	Guinea	NE	Niger
BE	Belgium	GR	Greece	NL	Netherlands
BF	Burkina Faso	HU	Hungary	NO	Norway
BG	Bulgaria	IE	Ireland	NZ	New Zealand
BJ	Benin	IT	Italy	PL	Poland
BR	Brazil	JP	Japan	PT	Portugal
BY	Belarus	KE	Kenya	RO	Romania
CA	Canada	KG	Kyrgyzstan	RU	Russian Federation
CF	Central African Republic	KP	Democratic People's Republic of Korea	SD	Sudan
CG	Congo	KR	Republic of Korea	SE	Sweden
CH	Switzerland	KZ	Kazakhstan	SI	Slovenia
CI	Côte d'Ivoire	LJ	Liechtenstein	SK	Slovakia
CM	Cameroon	LK	Sri Lanka	SN	Senegal
CN	China	LU	Luxembourg	TD	Chad
CS	Czechoslovakia	LV	Latvia	TG	Togo
CZ	Czech Republic	MC	Monaco	TJ	Tajikistan
DE	Germany	MD	Republic of Moldova	TT	Trinidad and Tobago
DK	Denmark	MG	Madagascar	UA	Ukraine
ES	Spain	ML	Mali	US	United States of America
FI	Finland	MN	Mongolia	UZ	Uzbekistan
FR	France			VN	Viet Nam
GA	Gabon				

## INTERNATIONAL SEARCH REPORT

Inter:    nal Application No  
PCT/US 94/01052

A. CLASSIFICATION OF SUBJECT MATTER  
IPC 5   C08F297/08   C08L23/08   C08F210/16

According to International Patent Classification (IPC) or to both national classification and IPC

## B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 5   C08F   C08L

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

## C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
P,X	WO,A,93 08221 (THE DOW CHEMICAL) 29 April 1993 see page 32, line 12 - line 22; claims 1,4,11,19,23,24 ---	1-21
A	EP,A,0 416 815 (THE DOW CHEMICAL) 13 March 1991 cited in the application see claims 1,9 ---	5-10, 17-21
A	WO,A,87 03610 (EXXON RESEARCH AND ENGINEERING) 18 June 1987 Abstract ---	1
A	EP,A,0 436 399 (MITSUI PETROCHEMICAL) 10 July 1991 see page 2, line 10 - page 3, line 32 -----	1

☐ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

## \* Special categories of cited documents :

- "A" document defining the general state of the art which is not considered to be of particular relevance
- "E" earlier document but published on or after the international filing date
- "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- "O" document referring to an oral disclosure, use, exhibition or other means
- "P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"&" document member of the same patent family

Date of the actual completion of the international search

6 July 1994

Date of mailing of the international search report

26. 07. 94

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patendaan 2  
NL - 2280 HV Rijswijk  
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,  
Fax: (+31-70) 340-3016

Authorized officer

Goovaerts, R

# INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/US 94/01052

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
WO-A-9308221	29-04-93	US-A- 5272236	21-12-93
		US-A- 5278272	11-01-94
		CA-A- 2120766	29-04-93
EP-A-0416815	13-03-91	AU-B- 645519	20-01-94
		AU-A- 6203990	07-03-91
		CA-A- 2024333	01-03-91
		JP-A- 3163088	15-07-91
		CN-A- 1049849	13-03-91
WO-A-8703610	18-06-87	US-A- 4874820	17-10-89
		AU-B- 593881	22-02-90
		AU-A- 6776987	30-06-87
		EP-A- 0230753	05-08-87
		JP-T- 63502191	25-08-88
		DE-A- 3682185	28-11-91
EP-A-0436399	10-07-91	JP-A- 3203909	05-09-91
		JP-A- 3203912	05-09-91
		JP-A- 3203905	05-09-91
		US-A- 5145818	08-09-92